

[illegible]

Non-Provisional Patent Application of:

For:

Apparatus and Methodology for Embossing Fibrous Webs Containing Contaminants

APPARATUS AND METHODOLOGY FOR EMBOSSING FIBROUS WEBS
CONTAINING CONTAMINANTS

5 Cross-Reference to Related Applications

This application claims the benefit of the filing date of U.S. Provisional Patent Application Serial No. 60/159,761, filed October 15, 1999.

Technical Field

10 The invention relates to embossing of paper products, for example, paper towels, toilet tissue and napkins, in which an improved embossing combination is used which is particularly suitable for the embossing of paper products made from recycled pulp.

15 Background of the Invention

Paper products, such as paper towels, napkins and toilet tissue are widely used on a daily basis for a variety of household needs. Typically, such products are formed of a fibrous elongated web which is either packaged in rolls or in a folded stack. The fibrous webs are usually embossed to increase the bulk of the tissue and to improve
20 the absorbency, softness and appearance of the product both as individual sheets, and in providing a uniform stack or roll package. Embossing can also aid in holding superposed plies of a web together. A commonly used embossing apparatus includes one or more steel embossing rollers having male protuberances thereon for forming the embossed pattern, and a corresponding steel roller which includes matched or
25 mated female recesses which are a three dimensional mirror image of the male protuberances. The web passes between the nip (gap) of the male and female embossing rollers such that the embossed pattern is imparted to the web.

Recently, environmental concerns have led to the use of greater amounts of recycled pulp in the production of paper products. However the economies of recycling make it practically impossible to remove all contaminants from the recycled pulp. In particular, recycled pulp often contains contaminants such as particles of glue and small pieces of plastic which adhere to the pulp, and which are known as "stickies". These contaminants when passed through the embossing rollers of paper production equipment may adhere to, or become lodged in, the protuberances or recesses of the rollers causing excess wear and possible damage to the embossing rollers, thus negating the savings had from the use of recycled materials. If on the other hand, the clearances embossing machinery are adjusted to accommodate possible contaminants in the recycled pulp, the qualities of the finished paper product may be adversely affected, which will render such recycled pulp based products less commercially attractive.

The present invention is directed to apparatus and methodology to provide embossing of recycled pulp without adversely affecting the processing machinery. This enables the recycled pulp to be embossed in a manner similar to that of non-recycled pulp which provides an absorbency, softness and appearance to the finished product which compares favorably to paper products made from non-recycled pulp. It has been found that recycled pulp can be embossed in a manner comparable to that of non-recycled pulp, even if it contains contaminants, if the embossing is carried out by matched embossing rollers in which one of the rollers is relatively soft Shore A (durometer) hardness of 40-65 and the other roller is relatively hard Shore A (durometer) hardness above about 90. The hard roll of the matched set may be a steel roll which is "off" of the Shore A hardness scale. As used herein, the terminology having a Shore A hardness of at least about 90 and the like or "greater than about 90" includes harder surfaces such as steel surfaces whether or not a different hardness scale would be applicable. As one of skill in the art will appreciate, a P&J hardness

scale is applicable to steel surfaces. Recycled pulp, even containing contaminants, may be embossed in this manner without causing excess wear or damage to the embossing rollers.

5 As used herein a matched set of embossing rollers means that the male embossing elements, carried by one roller, are engraved first and the female elements carried by the other rollers are subsequently made from the male elements, or vice versa, so that both elements are virtually inverse or reciprocal images of each other within the practicalities of manufacturing tolerances. This is in contrast to
10 “unmatched” embossing rollers in which the male and female embossing elements are not identical in shape, but still are positioned relative to each other in registry such that they engage.

 It is an object of the present invention to provide apparatus and methodology
15 for embossing webs that will avoid damage to the processing machinery should the web contain contaminating particles.

 It is an object of the present invention to provide apparatus and methodology for embossing paper products that will permit processing of recycled pulp without
20 causing excess wear or damage to the processing machinery.

 It is an object of the present invention to provide apparatus and methodology for embossing paper products that will permit older embossing machinery having matched embossing rollers to be retrofitted with a matched roller that can
25 accommodate pulp that may contain contaminants, such as recycled pulp.

0909210-104000

Background Art

U.S. Patent Nos. 5,503,896 and 5,529,563, both to *Veith et al.*, disclose methods for embossing webs using unmatched male and female embossing elements which are preferably made by laser engraving rubber embossing rolls (see, e.g., col. 3, lines 49-52 of U.S. Patent No. 5,503,896). The male and female embossing elements can be made of different materials. For example, the male elements can be made of steel, and the female elements can be composed of a deformable material, such as rubber, or vice versa (see, e.g., col. 4, lines 3-5 of U.S. Patent No. 5,503,896). The web can be any web suitable for embossing, including paper, tissue, nonwovens, films, laminates, combinations thereof and the like (see, e.g., col. 4, lines 10-13 of U.S. Patent No. 5,503,896).

U.S. Patent No. 5,727,458 to *Schulz* (the inventor herein) discloses an embossing method wherein two plies of web material are multilevel embossed between rigid engraved embossing rolls and backup embossing rolls. The backup embossing rolls can be composed of laser engraved rubber (see, e.g., col. 3, line 64 and col. 4, lines 56-57 and 67). The non-backup embossing rolls are generally composed of steel but may be substituted with laser-engraved rubber rolls (col. 4, lines 16-21). The backup embossing rolls may have a mirror image engraving of the embossing pattern on the non-backup embossing rolls (col. 4, lines 64-66). The embossing method can be used to make toilet tissue and paper towels (col. 3, lines 53-54).

United States Patent No. 5,269,983 to *Schulz* (the inventor herein) describes a method of embossing involving a mated pair of resilient and rigid embossing rolls. According to the '983 patent a laser can be utilized to form recesses in a resilient roll such that the resilient roll receives protuberances of a rigid male embossing roll when the rolls are placed in contact.

U.S. DEPARTMENT OF THE INTERIOR

U.S. DEPARTMENT OF THE INTERIOR

U.S. DEPARTMENT OF THE INTERIOR

U.S. DEPARTMENT OF THE INTERIOR

U.S. DEPARTMENT OF THE INTERIOR

U.S. DEPARTMENT OF THE INTERIOR

separation of the rolls, for example, to allow initial feeding and registration of the web between the rolls, and to urge the rolls together for the embossing operation. A nip 30 is formed between rollers 18,22 and can be adjusted by the hydraulic systems 26,28. Web 16 after being embossed, may then proceed to further web processing machinery such as a perforation roller 32.

In accordance with the present invention it has been found that if one of the matched pair of embossing rollers is formed from material that is less hard than the material of the other embossing roller, webs containing contaminants can be embossed without excess wear or damage to the embossing rollers. Specifically, the “hard” roller should have a Shore A hardness greater than about 95 (including steel), preferably 95-99 for laser engraved rolls. The “soft” roller should have a Shore A hardness of 40-95 and preferably in some embodiments 40-85 or 40-75 or even more preferably 40-65. The particular material used for either roller is not critical, for example, the hard roller could be steel, or a hard rubber or plastic. The soft roller is preferably natural rubber but can also be synthetic rubber or plastic. A Shore A hardness of 60-65 is particularly useful in some embodiments. A natural rubber can readily be made into a mirror image of the other roller by a laser process to “read” the protuberances or recesses and “burning” away the rubber. Such a process is described in United States Patent No. 5,269,983 issued to *Schulz* (the inventor herein), the disclosure of which is hereby incorporated by reference as if fully set forth herein.

In a particularly preferred method of the invention, there is provided a method for embossing a fibrous web containing contaminants to improve the bulk and softness of the web by passing the web through a nip formed by a pair of rotating rollers, wherein the contaminants will not damage the rollers, the method comprising the steps of a) providing a first embossing roller having an outer surface, said outer surface having a plurality of male protuberances thereon corresponding to a desired

2000 1999 1998 1997 1996 1995 1994 1993 1992 1991 1990 1989 1988 1987 1986 1985 1984 1983 1982 1981 1980 1979 1978 1977 1976 1975 1974 1973 1972 1971 1970 1969 1968 1967 1966 1965 1964 1963 1962 1961 1960 1959 1958 1957 1956 1955 1954 1953 1952 1951 1950 1949 1948 1947 1946 1945 1944 1943 1942 1941 1940 1939 1938 1937 1936 1935 1934 1933 1932 1931 1930 1929 1928 1927 1926 1925 1924 1923 1922 1921 1920 1919 1918 1917 1916 1915 1914 1913 1912 1911 1910 1909 1908 1907 1906 1905 1904 1903 1902 1901 1900 1899 1898 1897 1896 1895 1894 1893 1892 1891 1890 1889 1888 1887 1886 1885 1884 1883 1882 1881 1880 1879 1878 1877 1876 1875 1874 1873 1872 1871 1870 1869 1868 1867 1866 1865 1864 1863 1862 1861 1860 1859 1858 1857 1856 1855 1854 1853 1852 1851 1850 1849 1848 1847 1846 1845 1844 1843 1842 1841 1840 1839 1838 1837 1836 1835 1834 1833 1832 1831 1830 1829 1828 1827 1826 1825 1824 1823 1822 1821 1820 1819 1818 1817 1816 1815 1814 1813 1812 1811 1810 1809 1808 1807 1806 1805 1804 1803 1802 1801 1800 1799 1798 1797 1796 1795 1794 1793 1792 1791 1790 1789 1788 1787 1786 1785 1784 1783 1782 1781 1780 1779 1778 1777 1776 1775 1774 1773 1772 1771 1770 1769 1768 1767 1766 1765 1764 1763 1762 1761 1760 1759 1758 1757 1756 1755 1754 1753 1752 1751 1750 1749 1748 1747 1746 1745 1744 1743 1742 1741 1740 1739 1738 1737 1736 1735 1734 1733 1732 1731 1730 1729 1728 1727 1726 1725 1724 1723 1722 1721 1720 1719 1718 1717 1716 1715 1714 1713 1712 1711 1710 1709 1708 1707 1706 1705 1704 1703 1702 1701 1700 1699 1698 1697 1696 1695 1694 1693 1692 1691 1690 1689 1688 1687 1686 1685 1684 1683 1682 1681 1680 1679 1678 1677 1676 1675 1674 1673 1672 1671 1670 1669 1668 1667 1666 1665 1664 1663 1662 1661 1660 1659 1658 1657 1656 1655 1654 1653 1652 1651 1650 1649 1648 1647 1646 1645 1644 1643 1642 1641 1640 1639 1638 1637 1636 1635 1634 1633 1632 1631 1630 1629 1628 1627 1626 1625 1624 1623 1622 1621 1620 1619 1618 1617 1616 1615 1614 1613 1612 1611 1610 1609 1608 1607 1606 1605 1604 1603 1602 1601 1600 1599 1598 1597 1596 1595 1594 1593 1592 1591 1590 1589 1588 1587 1586 1585 1584 1583 1582 1581 1580 1579 1578 1577 1576 1575 1574 1573 1572 1571 1570 1569 1568 1567 1566 1565 1564 1563 1562 1561 1560 1559 1558 1557 1556 1555 1554 1553 1552 1551 1550 1549 1548 1547 1546 1545 1544 1543 1542 1541 1540 1539 1538 1537 1536 1535 1534 1533 1532 1531 1530 1529 1528 1527 1526 1525 1524 1523 1522 1521 1520 1519 1518 1517 1516 1515 1514 1513 1512 1511 1510 1509 1508 1507 1506 1505 1504 1503 1502 1501 1500 1499 1498 1497 1496 1495 1494 1493 1492 1491 1490 1489 1488 1487 1486 1485 1484 1483 1482 1481 1480 1479 1478 1477 1476 1475 1474 1473 1472 1471 1470 1469 1468 1467 1466 1465 1464 1463 1462 1461 1460 1459 1458 1457 1456 1455 1454 1453 1452 1451 1450 1449 1448 1447 1446 1445 1444 1443 1442 1441 1440 1439 1438 1437 1436 1435 1434 1433 1432 1431 1430 1429 1428 1427 1426 1425 1424 1423 1422 1421 1420 1419 1418 1417 1416 1415 1414 1413 1412 1411 1410 1409 1408 1407 1406 1405 1404 1403 1402 1401 1400 1399 1398 1397 1396 1395 1394 1393 1392 1391 1390 1389 1388 1387 1386 1385 1384 1383 1382 1381 1380 1379 1378 1377 1376 1375 1374 1373 1372 1371 1370 1369 1368 1367 1366 1365 1364 1363 1362 1361 1360 1359 1358 1357 1356 1355 1354 1353 1352 1351 1350 1349 1348 1347 1346 1345 1344 1343 1342 1341 1340 1339 1338 1337 1336 1335 1334 1333 1332 1331 1330 1329 1328 1327 1326 1325 1324 1323 1322 1321 1320 1319 1318 1317 1316 1315 1314 1313 1312 1311 1310 1309 1308 1307 1306 1305 1304 1303 1302 1301 1300 1299 1298 1297 1296 1295 1294 1293 1292 1291 1290 1289 1288 1287 1286 1285 1284 1283 1282 1281 1280 1279 1278 1277 1276 1275 1274 1273 1272 1271 1270 1269 1268 1267 1266 1265 1264 1263 1262 1261 1260 1259 1258 1257 1256 1255 1254 1253 1252 1251 1250 1249 1248 1247 1246 1245 1244 1243 1242 1241 1240 1239 1238 1237 1236 1235 1234 1233 1232 1231 1230 1229 1228 1227 1226 1225 1224 1223 1222 1221 1220 1219 1218 1217 1216 1215 1214 1213 1212 1211 1210 1209 1208 1207 1206 1205 1204 1203 1202 1201 1200 1199 1198 1197 1196 1195 1194 1193 1192 1191 1190 1189 1188 1187 1186 1185 1184 1183 1

15 16

From the point of view of the operation of the present invention it is irrelevant

whether the soft roller is the male roller (having the protuberances) or the female roller (containing the recesses). However from a practical viewpoint, it is likely to be less expensive to manufacture the female roller from rubber as this will generally require the removal of less material in the laser engraving process. The present invention may be easily implemented on older embossing equipment as the only change required is the replacement of one of the rollers in each embossing pair. The embossing roller's drive equipment, roller diameters and lengths as well as spacing will all remain unchanged. Furthermore, the size and type of the individual embossing elements are not limited by the present invention as both microembossing and macroembossing of fibrous webs can be undertaken.

The present invention is applicable as well to the updating of older embossing machinery having matched steel rollers. One of each of the matched pair of rollers can be removed, and by the laser reading and burning process described above, a new soft roller can be created to match the steel roller which may then be installed in the embossing equipment. In this manner older equipment otherwise unsuitable for the embossing of recycled material can be utilized to carry out the present invention thus extending the useful life of the equipment.

The present invention is also applicable to embossing machinery using unmatched rollers in which one of the rollers is replaced by a soft roller having the hardness parameters set forth above. Finally, the use of two matched soft rollers having a Shore A (durometer) hardness of 40-65 and a Shore A hardness of 60 and preferably of about 80 could also be used to emboss recycled pulp without damage from contaminants in accordance with the present invention.

The invention has been described with respect to preferred embodiments. However, as those skilled in the art will recognize, modifications and variations in the

For the past few years with the aid of the Government of the Republic of China, the Government of the People's Republic of China has been working to improve the living conditions of the people in the border areas of the Republic of China.